

ATK FOAM 30D - SPRAY POLYURETHANE FOAM (SPF) SYSTEM FOR THERMAL INSULATION (APPLIED DENSITY $\pm 30\text{-}33 \text{ KG/M}^3$)

ATK FOAM 30D polyurethane system for thermal insulation, is specifically formulated to apply foam with applied density around ($\pm 30\text{-}33 \text{ kg/m}^3$). Its application has to be done by the specific spray equipment.

USES

The polyurethane foam system ATK FOAM 30D can be used in these situations:

- complete and continuous system of thermal insulation in construction, industrial, farming or agricultural facilities.
- in applications inside ceilings, interior chambers facade, ventilated facades, partitions in general.

NOTE: For other applications / situations, please, consult our technical department.

applied density	30-33 kg/m ³
thermal conductivity	0,030 \pm 0,002 W/m·K
fire reaction	Euroclass E/B2
application	spray equipment

GENERAL FEATURES

- ATK FOAM 30D is a product with high insulating capacity, easy to apply covering all surfaces
- the application and training is done by our spray equipment GAMA or similar

it is free from harmful to the ozone layer, so do not promote the greenhouse effect (NOT contain HFCs, HCFCs, VOCs, etc ...).

ATK FOAM 30D system is 100% recyclable by mechanical means friendly to the environment

no gas collection for recycling and / or destruction is required

the heat transfer coefficient is unchanged from the placement and along the product life unlike the foam produced from gas low boiling.

it does not emit any substance to the environment once installed.

the properties of this polyurethane foam system allow it to adhere to any surface such as concrete, ceramic, metal, polyurethane foam, wood, acrylic paints (checking the situation of areas recommended).

The application of ATK FOAM 30D is completely continuous, instead of the classic non-continuous thermal insulation material, saving any kind of union between applications, and providing a optimum thermal insulation surface with high thermal insulation parameters

it has CE mark on the basis of a declaration of performance DoP prepared in accordance with EU regulation

PACKAGING

Metal drums of 250 kg for each product (polyol and isocyanate)

SHELF LIFE

POLYOL COMPOUND: 6 months(need to be shaken before use)

ISOCYANATE COMPOUND: 12 months

Temperature within 5 °C ~ 35 °C, provided it is stored in a dry place, non direct contact with sun.

APPLICATION METHOD

In general, you should take the following factors:

the application of polyurethane foam system ATK FOAM 30D, should be performed under non-presence of moisture or water from the support stand on which to apply either at the time of application as a posteriori.

the substrate must be clean and free of dust

perform successive layers of a thickness 1.5~3 cm each, until the desired thickness

ATK FOAM 30D adheres firmly on most common materials such as wood, plasterboard, steel, OSB, plywood, cement, inside masonry exterior plaster panels, and construction itself.

not shrinkage after performing the expansion.

reactivity times (in laboratory conditions): ◊

REACTING TIME: 3-6 seconds

EXPANDING TIME: 9-12 seconds

APPLICATION REQUIREMENTS (SPRAY EQUIPMENT)

For the formation, it is necessary to mix the two initial liquid components, isocyanates and amines by spray equipment GAMA or similar (proper maintenance and cleaning it is recommended). The general parameters for this material, will be the following:

The most general parameters of this equipment are as follows:

Heater isocyanate temperature: ±40-45 °C

Heater polioli temperature:±40-50°C

Hose temperature:±40-50°C

Pressure:100-125 bar

These temperature and pressure parameters have to be valued, ratified or be varied by the applicator, depending on the conditions of each climate zone, weather situation or as projection equipment specifications.

HANDLING

These safety recommendations for handling, are necessary for the implementation process as well as in the pre-and post, on exposure to the loading machinery.

Respiratory Protection: When handling or spraying use an air-purifying respirator.

Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking or smoking.

Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air. Waste: Waste generation should be avoided or minimized.

Incinerate under controlled conditions in accordance with local laws and national regulations.

Anyway, consult the material and safety data sheet of the product.

COMPLEMENTARY PRODUCTS

The ATK FOAM 30D system may be complemented with the following products as a means of protection or to improve its physical-mechanical properties depending on its exposure, the desired finish or the type of substrate.

ATK COAT LV: pure low viscosity polyurea. Approximate minimal consumption 1,5 kg/m²

ATK POL: single component polyurethane membrane for waterproof. Approximate minimal consumption 1,5 kg/m²

ATK TOP 2C: two component colored aliphatic polyurethane resin used to protect against UV rays, to use after ATK POL. Approximate minimal consumption 0.200-0.300 kg/m²

TECHNICAL DATA (ACCORDING DECLARATION OF PERFORMANCE)

Essential characteristics	Performance	Harmonized technical specification
Fire reaction	Euroclass E	EN 13501-1:2007
Water absorption (short term by partial immersion)	Wp <0,2 kg/m ²	EN 1609
Thermal resistance	See performance chart	EN 12667:2002
Water vapor permeability	Water vapor resistance factor: $\mu=70$	EN 12086
Compressive strength	No performance declared (NPD)	EN 826
Durability of reaction to fire against ageing/degradation	Reaction to fire does not decrease with time	EN 14315-1:2013
Durability of thermal resistance against ageing/degradation	See performance chart	EN 14315-1:2013
Durability of the compressive strength against aging / degradation	Compressive strength not decrease with time	EN 14315-1:2013
Continuous glowing combustion	No harmonized test method available	EN 14315-1:2013

To obtain more information, consult the full document Declaration of Performances of particular system (consult our technical department).